AUTHENTICATED
U.S. GOVERNMENT
INFORMATION
GPO

TABLE D–1—PERFORMANCE SPECIFICATIONS FOR PM_{10} SAMPLERS—Continued

Performance parameter	Units	Specification
2. 50 Percent cutpoint	μm	10±μ.5 μm aerodynamic diameter.
3. Precision	μg/m³ or percent	5 μg/m³ or 7 percent for three collocated samplers.
4. Flow rate stability	Percent	Average flow rate over 24 hours within ±5 percent of initial flow rate; all measured flow rates over 24 hours within ±10 percent of initial flow rate.

§ 53.41 Test conditions.

(a) Set-up and start-up of all test samplers shall be in strict accordance with the operating instructions specified in the manual referred to in § 53.4(b)(3).

(b) If the internal surface or surfaces of the candidate method's sampler inlet on which the particles removed by the inlet are collected is a dry surface (i.e., not normally coated with oil or grease), those surfaces shall be cleaned prior to conducting wind tunnel tests with solid particles.

(c) Once the test sampler or samplers have been set up and the performance tests started, manual adjustment shall be permitted only between test points for the sampling effectiveness and 50 percent cutpoint tests or between test days for the precision and flow rate stability tests. The manual adjustments and any periodic maintenance shall be limited to only those procedures prescribed in the manual referred to in § 53.4(b)(3). The submitted records shall show clearly when any manual adjustment or periodic maintenance was made and shall describe the operations performed.

(d) If a test sampler malfunctions during any of the sampling effectiveness and 50 percent cutpoint tests, that test run shall be repeated. If a test sampler malfunctions during any of the precision and flow rate stability tests, that day's test shall be repeated. A detailed explanation of all malfunctions and the remedial actions taken shall be submitted to EPA with the application.

§ 53.42 Generation of test atmospheres for wind tunnel tests.

(a) A vibrating orifice aerosol generator shall be used to produce monodispersed liquid particles of oleic acid tagged with uranine dye and monodispersed solid particles of ammonium fluoroscein with equivalent aerodynamic diameters as specified in table D–2. The geometric standard deviation for each particle size and type generated shall not exceed 1.1 (for primary particles) and the proportion of multiplets (doublets and triplets) in a test particle atmosphere shall not exceed 10 percent. The particle delivery system shall consist of a blower system and a wind tunnel having a test section of sufficiently large cross-sectional area such that the test sampler, or portion thereof, as installed in the test section for testing, blocks no more than 15 percent of that area. To be acceptable, the blower system must be capable of achieving uniform wind speeds at the speeds specified in table D–2.

TABLE D–2—PARTICLE SIZES AND WIND SPEEDS FOR SAMPLING EFFECTIVENESS TESTS

Particle size (μm)[a]	Wind speed (km/hr)		
	2	8	24
3±0.5	l	l	l
5±0.5	l	l	l
7±0.5	l	l	l
9±0.5	l	l	l
10±0.5	l	l	l
11±0.5	l	l	l
13±1.0	l	l	l
15±1.0	l	l	l
20±1.0	l	l	l
25±1.0	l	l/s	l/s

[a] Mass median aerodynamic diameter.
l = liquid particle.
s=solid particle.
Number of liquid particle test points (minimum of 3 replicates for each combination of particle size and wind speed): 90.
Number of solid particle test points (minimum of 3 replicates for each combination of particle size and wind speed): 6.
Total number of test points: 96.

(b) The size of the test particles delivered to the test section of the wind tunnel shall be established using the operating parameters of the vibrating orifice aerosol generator and shall be verified during the tests by microscopic examination of samples of the particles collected on glass slides or other suitable substrates. When sizing liquid particles on glass slides, the slides should be pretreated with an