



United States Department of Commerce
Technology Administration
National Institute of Standards and Technology

NIST Technical Note 1414

Liquid-Nitrogen-Cooled High T_c Electrical Substitution Radiometer as a Broadband IR Transfer Standard

J. P. Rice and Z. M. Zhang

The National Institute of Standards and Technology was established in 1988 by Congress to “assist industry in the development of technology . . . needed to improve product quality, to modernize manufacturing processes, to ensure product reliability . . . and to facilitate rapid commercialization . . . of products based on new scientific discoveries.”

NIST, originally founded as the National Bureau of Standards in 1901, works to strengthen U.S. industry’s competitiveness; advance science and engineering; and improve public health, safety, and the environment. One of the agency’s basic functions is to develop, maintain, and retain custody of the national standards of measurement, and provide the means and methods for comparing standards used in science, engineering, manufacturing, commerce, industry, and education with the standards adopted or recognized by the Federal Government.

As an agency of the U.S. Commerce Department’s Technology Administration, NIST conducts basic and applied research in the physical sciences and engineering, and develops measurement techniques, test methods, standards, and related services. The Institute does generic and precompetitive work on new and advanced technologies. NIST’s research facilities are located at Gaithersburg, MD 20899, and at Boulder, CO 80303. Major technical operating units and their principal activities are listed below. For more information contact the Public Inquiries Desk, 301-975-3058.

Office of the Director

- Advanced Technology Program
- Quality Programs
- International and Academic Affairs

Technology Services

- Manufacturing Extension Partnership
- Standards Services
- Technology Commercialization
- Measurement Services
- Technology Evaluation and Assessment
- Information Services

Materials Science and Engineering Laboratory

- Intelligent Processing of Materials
- Ceramics
- Materials Reliability¹
- Polymers
- Metallurgy
- Reactor Radiation

Chemical Science and Technology Laboratory

- Biotechnology
- Chemical Kinetics and Thermodynamics
- Analytical Chemical Research
- Process Measurements²
- Surface and Microanalysis Science
- Thermophysics²

Physics Laboratory

- Electron and Optical Physics
- Atomic Physics
- Molecular Physics
- Radiometric Physics
- Quantum Metrology
- Ionizing Radiation
- Time and Frequency¹
- Quantum Physics¹

Manufacturing Engineering Laboratory

- Precision Engineering
- Automated Production Technology
- Intelligent Systems
- Manufacturing Systems Integration
- Fabrication Technology

Electronics and Electrical Engineering Laboratory

- Microelectronics
- Law Enforcement Standards
- Electricity
- Semiconductor Electronics
- Electromagnetic Fields¹
- Electromagnetic Technology¹
- Optoelectronics¹

Building and Fire Research Laboratory

- Structures
- Building Materials
- Building Environment
- Fire Safety
- Fire Science

Computer Systems Laboratory

- Office of Enterprise Integration
- Information Systems Engineering
- Systems and Software Technology
- Computer Security
- Systems and Network Architecture
- Advanced Systems

Computing and Applied Mathematics Laboratory

- Applied and Computational Mathematics²
- Statistical Engineering²
- Scientific Computing Environments²
- Computer Services
- Computer Systems and Communications²
- Information Systems

¹At Boulder, CO 80303.

²Some elements at Boulder, CO 80303.

NIST Technical Note 1414

Liquid-Nitrogen-Cooled High T_c Electrical Substitution Radiometer as a Broadband IR Transfer Standard

J. P. Rice and Z. M. Zhang

Radiometric Physics Division
Physics Laboratory
National Institute of Standards and Technology
Gaithersburg, MD 20899-0001

January 1996



U.S. Department of Commerce

Ronald H. Brown, Secretary

Technology Administration

Mary L. Good, Under Secretary for Technology

National Institute of Standards and Technology

Arati Prabhakar, Director

National Institute of Standards
and Technology
Technical Note 1414
Natl. Inst. Stand. Technol.
Tech. Note 1414
14 pages (January 1996)
CODEN: NTNOEF

U.S. Government Printing Office
Washington: 1996

For sale by the Superintendent of
Documents
U.S. Government Printing Office
Washington, DC 20402

Table of Contents

Abstract	1
1. Introduction	2
2. Absolute Electrical-Substitution Radiometers	2
3. Transfer Standard ESR at 77 K	3
3.1 Design	3
3.2 Theoretical Performance Analysis	5
3.2.1 Temperature Stability	6
3.2.2 Operating Point	6
3.2.3 Ultimate Limits of Sensitivity	7
4. Conclusion	8
5. References	8

List of Figures

1. A map of infrared transfer standard radiometers that exist or are being developed at NIST, showing where the proposed broadband radiometer would fit in.	10
2. Proposed design for a liquid-nitrogen-cooled high- T_c ESR. ...	11

Liquid-Nitrogen-Cooled High T_c Electrical Substitution Radiometer as a Broadband IR Transfer Standard

J. P. Rice and Z. M. Zhang

Radiometric Physics Division, National Institute of Standards and
Technology, Gaithersburg, MD 20899, USA

Abstract

A requirement exists for broadband radiometers that can be used to transfer NIST infrared radiometric scales to calibration laboratories elsewhere. We discuss the design of a liquid-nitrogen-cooled transfer standard radiometer that represents a practical tradeoff between room-temperature and liquid-helium-cooled radiometers. The detector utilizes high- T_c superconductors as temperature sensors for increased sensitivity. Such sensors have already been shown to enable temperature regulation of 100 μ K peak-to-peak at 85 K, and have the potential for further improvements by three orders of magnitude. Electrical substitution is used to linearize the response over the dynamic range and to remove susceptibility to sensor aging effects. A reflective light trap is used in conjunction with a gold-black coating on the sensor to enable flat spectral response over a broad infrared band. Ultimately, the radiometer could have a noise-equivalent power of 10 pW/Hz^{1/2}, which is sufficient sensitivity to perform 1% uncertainty scale transfers over the milliwatt to nanowatt power ranges.

Keywords

infrared, radiometer, electrical-substitution, high- T_c superconductors, temperature control

1. INTRODUCTION

Currently there are several infrared transfer radiometers that have been developed or are being developed at NIST for various purposes, as shown in Figure 1. Although all these radiometers can be used to transfer a radiometric scale (i.e., radiant power, irradiance, or radiance) they differ in many other respects. Wavelength coverage, temperature of operation, power range, and projected uncertainties in the transfer of radiometric scale are some of the differences. In Figure 1 we have grouped the IR transfer radiometers according to wavelength and temperature of operation. This is a simplified way of demonstrating where requirements are being fulfilled and where there is important need for more development. Electrically calibrated pyroelectric detectors, originally developed at NIST during the 1970's and now commercially available, are the least sensitive but most convenient because they operate at room temperature [1]. At the other extreme are blocked impurity band (BIB) detectors and silicon bolometers. Custom-made BIB detectors are currently being characterized as transfer standards for low-background infrared detection [2]. A silicon bolometer device has been characterized recently as a transfer standard for the IR detector comparator facility at NIST [3]. BIB detectors and silicon bolometers are the most sensitive but must be cooled to temperatures near that of liquid helium. At liquid-nitrogen temperatures (77K), transfer radiometers based on InSb are being developed at NIST [4], but they are limited to wavelengths less than 5 μm . The radiometer proposed here would fulfill the need for a broadband radiometer at 77 K for wavelengths from 5 μm to 20 μm , with the required sensitivity level for most radiometric applications.

2. ABSOLUTE ELECTRICAL-SUBSTITUTION RADIOMETERS

Electrical-substitution radiometers (ESR) are commonly used to establish absolute detector-based radiometric scales [5,6]. They operate by heating a thermally isolated optical absorber with radiant power and then with electrical power in alternate cycles. Using precision thermometry to ensure that an equivalent temperature rise is attained by the two heating methods, a measurement of the electrical power provides an accurate measurement of the radiant power. While some ESR's have

been designed to work at ambient temperatures, the most sensitive instruments are cryogenic radiometers cooled with liquid helium. At liquid-helium temperatures (< 4.2 K) the heat capacity of materials such as copper is very low. Thus the optical absorber can be made as a high emissivity cavity while the time constant can be kept short enough to complete a measurement cycle in a reasonable time. Such radiometers, often called active-cavity radiometers, are absolute radiometers since essentially all of the radiative power is converted to heat which is measured by comparison to electrical power. Since they require liquid helium for their operation, however, their use as portable transfer standard radiometers for transferring radiometric scales is fraught with difficulties of using bulky expensive equipment and bearing associated costs.

3. TRANSFER STANDARD ESR AT 77 K

As transfer standards, the operation of an ESR near the temperature of liquid nitrogen (77 K) would offer many advantages. Here the purpose of electrical substitution is not to establish an absolute scale, but rather to provide linearity of the radiometer over a wide dynamic range to enable an accurate transfer of a radiometric scale from a primary facility to a secondary facility. The advantage over a liquid-helium-cooled radiometer is ease of use and operating cost. The heat of vaporization per volume of liquid nitrogen is 59 times higher than that of liquid helium [7], and the price per volume of liquid nitrogen is typically about 60 times lower. Thus the total cryogen cost during operation is thousands of times cheaper for liquid nitrogen operation than for liquid helium operation. The advantage over an ambient temperature radiometer is that cooling from 300 K to 77 K reduces the background radiance by a factor of 230. Thus as a transfer radiometer in the thermal infrared, where the precision of a liquid-helium-cooled radiometer is often not necessary but room-temperature background is not acceptable, a liquid-nitrogen-cooled radiometer would be a welcome addition to satisfy the needs.

3.1 DESIGN

A simplified design for a liquid-nitrogen-cooled ESR to be developed is illustrated in Figure 2. It consists of a temperature sensor and a heater

integrated onto a thin sapphire (or silicon micromachined) disk thermally isolated from a heat sink. The disk is coated with a low-mass-density infrared absorbing coating such as gold-black. The temperature sensor is a thin film of $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ (YBCO) grown on the sapphire with a buffer layer of CeO_2 . The heater is a thin film of a resistive alloy such as Ni-Cr. Both the YBCO sensor and the heater are patterned as four-wire resistors.

The operation of the radiometer is as follows. YBCO is a high- T_c superconductor having a sharp resistive superconducting transition near 90 K, as shown in the inset. Thus it provides a very sensitive temperature sensor if its temperature is held near the midpoint of the resistive transition, which we call the operating point. A feedback circuit is used to supply the appropriate power to the heater to keep the sensor, and hence the thermally isolated disk, at the operating point. The feedback electronics consist of an ac bridge to monitor the four-wire resistance of the YBCO sensor, a lock-in amplifier to demodulate the ac signal into a dc signal, and a dc amplifier to drive the heater. The electrical power supplied to the heater is measured as the product of the voltage across the heater and the current through it. With the radiometer shutter closed, a certain amount of electrical power is required to keep the sensor at the operating point. When the shutter is opened, the radiant power illuminating the disk will change, and hence the electrical power supplied to the heater will change in order to keep the sensor at the operating point. The difference in electrical power supplied to the heater is then a measure of the difference in radiant power absorbed by the disk between the shutter open and shutter closed conditions. This balancing between radiant and electrical power provides an inherently linear measure of the radiant power over the full dynamic range of the instrument.

Heat capacities of materials are relatively high at liquid nitrogen temperatures, so it is necessary to minimize the sizes of components which potentially heat and cool during measurements. Thus in the design above we have incorporated a gold-coated reflective light trap in conjunction with the gold-black coating on the disk. In this design, only the disk heats. The radiation enters through a hole in the reflective light trap and most rays are absorbed by the gold-black. The reflective light trap redirects scattered rays toward the gold-black, thus increasing the chances that they will ultimately be absorbed on the disk. It has been shown that the spectral response of gold-black in such a reflective light trap is much flatter than that for gold-black alone [8].

3.2 THEORETICAL PERFORMANCE ANALYSIS

As a first example, consider a design where the disk is at 90 K and the heat sink is held at 77 K by good thermal contact with the nitrogen bath. The maximum power $P_{\max}$ that can be measured is determined by

$$P_{\max} = G\Delta T, \quad (1)$$

where G is the thermal conductance between the disk and heat sink and ΔT is the maximum allowable temperature difference between the disk and heat sink. Assume that $G = 10^{-4}$ W/K (a practical value) and $\Delta T = 10$ K. Then $P_{\max} = 1$ mW, which corresponds roughly to the typical laser power routinely used for calibrations in the High Accuracy Cryogenic Radiometer (HACR), a liquid-helium ESR which serves as the primary standard for optical power in the Radiometric Physics Division at NIST.

The time constant for temperature changes is given by

$$\tau = C/G, \quad (2)$$

where C is the heat capacity of the thermally-isolated components. Assuming that the sapphire disk is 5 mm in diameter, 25 μm thick, and dominates the heat capacities of the thin films, $C \approx 0.15$ mJ/K at 90 K. This gives $\tau = 1.5$ s, which is a practical value.

To estimate $P_{\min}$, the minimum power that can be calibrated at the desired accuracy, we need to know the noise floor power P_{nf} . A typical measurement cycle would take place over a time interval on the order of 100 time-constants. The ability to control temperature over this time interval plays a role in determining P_{nf} according to

$$P_{\text{nf}} = G\sqrt{(\delta T_d)^2 + (\delta T_h)^2}, \quad (3)$$

where δT_d and δT_h are the temperature stability of the disk and heat sink, respectively. As discussed below, we estimate $\delta T_d \approx \delta T_h \approx 100$ μK over several minutes. Thus Equation (3) yields $P_{\text{nf}} = 1.4 \times 10^{-8}$ W. To allow for a relative expanded uncertainty of 1%, $P_{\min} = 100P_{\text{nf}} = 1.4$ μW . Thus, this transfer radiometer would enable a scale comparison from milliwatt power levels to microwatt power levels at the 1% relative expanded

uncertainty level. This assumes, of course, that other considerations do not degrade the accuracy. This level of sensitivity is roughly equivalent to that quoted for commercially available room-temperature electrically calibrated pyroelectric radiometers [9]. If temperature stability can be made even better, as we discuss below, $P_{\min}$ will likewise be lower and the dynamic range will increase.

3.2.1 TEMPERATURE STABILITY

We now consider the temperature stability attainable using YBCO sensors. Peak-to-peak temperature stability of 100 μK over several minutes has recently been achieved by the group of D. Robbes using a YBCO strip and heater in a temperature control feedback loop [10]. The stage being controlled was a cold finger made of an aluminum alloy having $C = 0.49 \text{ J/K}$ in thermal contact with a liquid-nitrogen bath by a G of 50 mW/K. This stage is akin to what would be the heat sink in our radiometer above. The stability under temperature control was several times better than that achieved by having the cold finger in contact with nitrogen and without controlling the temperature. This suggests that a design involving independent temperature control for both the disk and the heat sink, with a superconductive sensor on both disk and heat sink, would be superior, since by controlling the temperature of the heat sink the fluctuations of liquid nitrogen temperature from effects such as atmospheric pressure fluctuations would be greatly reduced. The change in the boiling point of liquid nitrogen with pressure is about 83 $\mu\text{K/Pa}$ (11 mK/Torr) [7]. Since the disk is further isolated, we would expect to attain as good or better stability for the disk temperature. Thus the assumption of 100 μK temperature stability for both disk and heat sink is conservative.

3.2.2 OPERATING POINT

In the discussion above, we have assumed that the operating point for each sensor is at the midpoint of the YBCO resistive transition. In order to maintain a temperature difference of $\Delta T = 10 \text{ K}$ between heat sink and disk, the two superconductive sensors must have T_c 's that differ by 10 K. This presents a challenge, since pure YBCO films typically have a 1 K wide transition at 90 K. The heat sink sensor, which would require T_c

near 80 K, would need to be made from either YBCO doped with impurities to reduce T_c or another high T_c material. An alternative solution is suggested by the experiments of Robbes, where the temperature dependence of the critical current just below T_c is used as a thermometer [10]. The critical current (I_c) is the current that drives the sensor from the superconducting to the normal state. It is a strong function of temperature just below T_c , dropping to zero at T_c . Using a bias reversal technique and the appropriate compensation electronics, Robbes' group demonstrated a method for using this sensitive variation of I_c with temperature to measure temperature over a range of about 5 K below T_c in YBCO. The 100 μ K temperature stability quoted above was achieved using this technique a few Kelvin below T_c . Thus, since the operating point does not have to be at T_c , YBCO sensors having identical values of T_c may be useable as both the disk and heat sink sensors.

3.2.3 ULTIMATE LIMITS OF SENSITIVITY

From a consideration of the minimum detectable temperature fluctuation, or noise equivalent temperature (NET), we can determine the ultimate limits on temperature stability and sensitivity. The lowest values of NET measured until now on YBCO sensors are below

$1 \times 10^{-7} \text{ K}/\sqrt{\text{Hz}}$ [11,12]. This is close to the so-called phonon noise contribution to the NET, which is a result of thermodynamic temperature fluctuations:

$$\text{NET}_{\text{ph}} = \sqrt{\frac{4k_B T^2}{G}} \quad (4)$$

With $G = 10^{-4} \text{ W/K}$ and $T = 90 \text{ K}$ this is $7 \times 10^{-8} \text{ K}/\sqrt{\text{Hz}}$. Thus, for a bandwidth of 1 Hz the ultimate temperature stability is about 70 nK, so it is feasible that we could improve on the 100 μ K stability used in our estimate above by more than three orders of magnitude [13]. A temperature stability of 70 nK would lead to a P_{nf} of 10 pW, surpassing the sensitivity of the electrically calibrated pyroelectric detectors by a factor of 1000. At this level of performance, scale comparisons at the 1% relative expanded uncertainty level could be made between milliwatt power levels and nanowatt power levels.

4. CONCLUSION

We have outlined the design and estimated the performance level for a liquid-nitrogen-cooled high- T_c superconductive infrared radiometer that offers a practical tradeoff between cost, convenience, and sensitivity. It will be a broadband detector, will have an ultimate sensitivity of as low as 10 pW, and will be capable of measuring radiant power levels up to 1 mW.

5. REFERENCES

- [1] R. J. Phelan, J. H. Lehman, and D. R. Larson, "Electrically calibrated pyroelectric detector - refinements for improved optical power measurements," SPIE 2022, 160 (1993).
- [2] S. L. Lorentz, Radiometric Physics Division, NIST, Gaithersburg, (private communication).
- [3] G. Eppeldauer, A. L. Migdall, and C. L. Cromer, "Characterization of a high sensitivity composite silicon bolometer," Metrologia 30, 317-320 (1993).
- [4] G. Eppeldauer, Radiometric Physics Division, NIST, Gaithersburg, (private communication).
- [5] R. U. Datla, K. Stock, A. C. Parr, C. C. Hoyt, P. J. Miller, and P. V. Foukal, "Characterization of an absolute cryogenic radiometer (ACR) as a standard detector for radiant power measurements," Appl. Opt. 31, pp. 7219-7225 (1992).
- [6] J. E. Martin, N. P. Fox, and P. J. Key, "A cryogenic radiometer for absolute radiometric measurements," Metrologia 21, 147-155 (1985).
- [7] Experimental techniques in low-temperature physics by G. K. White (Oxford, New York, 1968).

- [8] G. W. Day, C. A. Hamilton, and K. W. Pyatt, "Spectral reference detector for the visible to 12 μm region; convenient, spectrally flat," Appl. Opt. 15, 1865 (1976).
- [9] Rs-5900 ECPR Product Literature, Laser Probe Inc., Utica, New York.
- [10] E. Lesquey, C. Gunther, S. Flament, R. Desfeux, J. F. Hamet, and D. Robbes, "Progress towards a low noise temperature regulation using a superconductive high T_c microbridge," preprint submitted to the 1994 Applied Superconductivity Conference.
- [11] J. C. Brasunas and B. Lakew, "Transition-edge noise in $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ thin films before and after exposure to ionizing radiation," J. Appl. Phys. 75, 7565 (1994).
- [12] S. Verghese, P. L. Richards, K. Char, D. K. Fork, and T. H. Geballe, "Feasibility of infrared imaging arrays using high- T_c superconducting bolometers," J. Appl. Phys. 71, 2491 (1992).
- [13] D. G. McDonald, Boulder Metric, Boulder, Colorado (private communication).




Figure 1. A map of infrared transfer standard radiometers that exist or are being developed at NIST, showing where the proposed broadband radiometer would fit in.




Figure 2. Proposed design for a liquid-nitrogen-cooled high T_c ESR.

NIST Technical Publications

Periodical

Journal of Research of the National Institute of Standards and Technology—Reports NIST research and development in those disciplines of the physical and engineering sciences in which the Institute is active. These include physics, chemistry, engineering, mathematics, and computer sciences. Papers cover a broad range of subjects, with major emphasis on measurement methodology and the basic technology underlying standardization. Also included from time to time are survey articles on topics closely related to the Institute's technical and scientific programs. Issued six times a year.

Nonperiodicals

Monographs—Major contributions to the technical literature on various subjects related to the Institute's scientific and technical activities.

Handbooks—Recommended codes of engineering and industrial practice (including safety codes) developed in cooperation with interested industries, professional organizations, and regulatory bodies.

Special Publications—Include proceedings of conferences sponsored by NIST, NIST annual reports, and other special publications appropriate to this grouping such as wall charts, pocket cards, and bibliographies.

National Standard Reference Data Series—Provides quantitative data on the physical and chemical properties of materials, compiled from the world's literature and critically evaluated. Developed under a worldwide program coordinated by NIST under the authority of the National Standard Data Act (Public Law 90-396). NOTE: The Journal of Physical and Chemical Reference Data (JPCRD) is published bimonthly for NIST by the American Chemical Society (ACS) and the American Institute of Physics (AIP). Subscriptions, reprints, and supplements are available from ACS, 1155 Sixteenth St., NW, Washington, DC 20056.

Building Science Series—Disseminates technical information developed at the Institute on building materials, components, systems, and whole structures. The series presents research results, test methods, and performance criteria related to the structural and environmental functions and the durability and safety characteristics of building elements and systems.

Technical Notes—Studies or reports which are complete in themselves but restrictive in their treatment of a subject. Analogous to monographs but not so comprehensive in scope or definitive in treatment of the subject area. Often serve as a vehicle for final reports of work performed at NIST under the sponsorship of other government agencies.

Voluntary Product Standards—Developed under procedures published by the Department of Commerce in Part 10, Title 15, of the Code of Federal Regulations. The standards establish nationally recognized requirements for products, and provide all concerned interests with a basis for common understanding of the characteristics of the products. NIST administers this program in support of the efforts of private-sector standardizing organizations.

Order the following NIST publications—FIPS and NISTIRs—from the National Technical Information Service, Springfield, VA 22161.

Federal Information Processing Standards Publications (FIPS PUB)—Publications in this series collectively constitute the Federal Information Processing Standards Register. The Register serves as the official source of information in the Federal Government regarding standards issued by NIST pursuant to the Federal Property and Administrative Services Act of 1949 as amended, Public Law 89-306 (79 Stat. 1127), and as implemented by Executive Order 11717 (38 FR 12315, dated May 11, 1973) and Part 6 of Title 15 CFR (Code of Federal Regulations).

NIST Interagency Reports (NISTIR)—A special series of interim or final reports on work performed by NIST for outside sponsors (both government and nongovernment). In general, initial distribution is handled by the sponsor; public distribution is by the National Technical Information Service, Springfield, VA 22161, in paper copy or microfiche form.

U.S. Department of Commerce
National Institute of Standards
and Technology
Gaithersburg, MD 20899-0001

Official Business
Penalty for Private Use \$300