

6340

1310 D&T  
= 6340

# NATIONAL BUREAU OF STANDARDS REPORT

6340

A SURVEY OF SOME MAGNESIUM FIRE PROBLEMS

by  
A. F. Robertson



U. S. DEPARTMENT OF COMMERCE  
NATIONAL BUREAU OF STANDARDS

## THE NATIONAL BUREAU OF STANDARDS

### Functions and Activities

The functions of the National Bureau of Standards are set forth in the Act of Congress, March 3, 1901, as amended by Congress in Public Law 619, 1950. These include the development and maintenance of the national standards of measurement and the provision of means and methods for making measurements consistent with these standards; the determination of physical constants and properties of materials; the development of methods and instruments for testing materials, devices, and structures; advisory services to Government Agencies on scientific and technical problems; invention and development of devices to serve special needs of the Government; and the development of standard practices, codes, and specifications. The work includes basic and applied research, development, engineering, instrumentation, testing, evaluation, calibration services, and various consultation and information services. A major portion of the Bureau's work is performed for other Government Agencies, particularly the Department of Defense and the Atomic Energy Commission. The scope of activities is suggested by the listing of divisions and sections on the inside of the back cover.

### Reports and Publications

The results of the Bureau's work take the form of either actual equipment and devices or published papers and reports. Reports are issued to the sponsoring agency of a particular project or program. Published papers appear either in the Bureau's own series of publications or in the journals of professional and scientific societies. The Bureau itself publishes three monthly periodicals, available from the Government Printing Office: The Journal of Research, which presents complete papers reporting technical investigations; the Technical News Bulletin, which presents summary and preliminary reports on work in progress; and Basic Radio Propagation Predictions, which provides data for determining the best frequencies to use for radio communications throughout the world. There are also five series of nonperiodical publications: The Applied Mathematics Series, Circulars, Handbooks, Building Materials and Structures Reports, and Miscellaneous Publications.

Information on the Bureau's publications can be found in NBS Circular 460, Publications of the National Bureau of Standards (\$1.25) and its Supplement (\$0.75), available from the Superintendent of Documents, Government Printing Office, Washington 25, D. C.

Inquiries regarding the Bureau's reports should be addressed to the Office of Technical Information, National Bureau of Standards, Washington 25, D. C.

# NATIONAL BUREAU OF STANDARDS REPORT

NBS PROJECT  
1002-12-4873

March 16, 1959

NBS REPORT  
6340

## A SURVEY OF SOME MAGNESIUM FIRE PROBLEMS

by  
A. F. Robertson

for  
Bureau of Ships  
Department of the Navy  
Code 538  
Index Number NS-183-001

### IMPORTANT NOTICE

NATIONAL BUREAU OF  
intended for use within t  
to additional evaluation a  
listing of this Report, eith  
the Office of the Director,  
however, by the Governme  
to reproduce additional c

Approved for public release by the  
Director of the National Institute of  
Standards and Technology (NIST)  
on October 9, 2015.

r progress accounting documents  
formally published it is subjected  
ig, reproduction, or open-literature  
nission is obtained in writing from  
Such permission is not needed,  
lly prepared if that agency wishes



U. S. DEPARTMENT OF COMMERCE  
NATIONAL BUREAU OF STANDARDS



## A SURVEY OF SOME MAGNESIUM FIRE PROBLEMS

### ABSTRACT

At normal pressures magnesium appears to burn in the vapor phase resulting from vaporization of the metal at temperatures below that observed during combustion. Although the heat of combustion is quite comparable to that of wood, the reaction temperature is much higher.

The high temperature existing during such fires can result in flash dissociation of water applied to them. The resulting flareup of the fire and apparent explosion may scatter the molten metal, spreading the fire.

Ignition of magnesium may be controlled by consideration of the relative geometry of the metal and the ignition source, the objective being to dissipate heat more rapidly than the rate of its supply. The use of an anodic coating is suggested as likely to result in greatly increased periods between fire exposure and ignition.

Techniques for extinguishment of magnesium fires appear to have been based largely on the formation of a protecting blanket around the burning magnesium with concurrent cooling and possibly formation of secondary fires. Experiments performed with small fires suggest the possible use of CO<sub>2</sub> or N<sub>2</sub> for control purposes. The heat of reaction of magnesium with these gases amounts to about 60 and 25 percent, respectively, of that for the straight oxidation process. This together with the fact that reaction temperatures are greatly reduced should, under certain conditions, permit their effective use in limiting temperatures experienced with magnesium fires. Liquid nitrogen, when properly applied, provides an effective extinguishing agent.

### Physical Properties

Magnesium is a light, white tough metal which tarnishes with an oxide film on exposure to air. It is one-third lighter than aluminum and in its alloys has been widely used in aircraft construction. Recently it has been introduced for fabrication of portable power tools and other implements. Pure magnesium has a specific gravity of 1.74 at 68°F, melts at 1202°F (650°C) and boils at 2043°F (1117°C) and atmospheric pressure [17]. As a solid, it exhibits a vapor pressure of 0.01 atmosphere [2] at a temperature of 1126°F (608°C). In the liquid form the vapor pressure is reported [3] as 5 mm at 1207°F (653°C) and 100 mm at 1618°F (881°C).



## Reactivity

Its affinity for oxygen is so great that heavy metal parts, when once ignited, burn with great vigor and may be difficult to extinguish. In the finely ground form it may burn with explosive violence. Its combustion in air is accompanied with liberation of an intense white light. This radiation from burning magnesium may be considered more as an indication of the high temperature at which the oxidation reaction takes place than as an indication of high heat of combustion. This latter is about 10,650 BTU/lb<sup>4</sup> and thus is of the same order of magnitude as for many other combustibles. The temperatures developed during combustion of magnesium at atmospheric pressure are reported as being usually between the boiling point of the metal 2025°F (1107°C) and the melting temperature of the oxide 5072°F (2800°C)<sup>4</sup>.

Because magnesium boils at a temperature below that developed during its combustion, a flame of considerable size is usually developed. The dazzling white light accompanying this flame is probably largely a result of the high temperature and the resulting emission from thermally excited oxide particles.

## Ignition

The ignition of magnesium, as of other combustibles, becomes possible only when, among other requirements, the rate of heat generation exceeds that of heat loss. Thus, with commonly available ignition sources, the physical form of the metal will influence the ease with which it may be ignited. Finely divided material is readily ignited with only small ignition sources while heavy magnesium objects usually require large area ignition sources. The high thermal conductivity of the alloys and pure magnesium <sup>5</sup> 320 to 1092 BTU in/hr°F ft<sup>2</sup> (0.11 to 0.376 cal/cm°C sec) assists in the dissipation of heat from ignition sources which are small compared to the size of the metal part being heated.

Fassell, et al <sup>6</sup> have studied the self-ignition behavior of over 100 magnesium alloys. They report ignition temperatures in the range of 864 to 1200°F (462 - 649°C). Their measurements were made on small cylindrical specimens heated within an oven. In performing the experiments, the temperature of the specimen at a time just prior to that at which its rate of temperature change rapidly increased, was taken as the ignition temperature. This technique would be expected to and indeed appears to have resulted in temperatures slightly higher than those measured by Setchkin <sup>7</sup> in which specimens were exposed for prolonged periods at essentially constant temperature. During such tests, it would be expected that the surface to volume ratio of the metal specimen would be an important variable affecting the ignition





temperature observed. It seems quite likely that under suitable conditions the ignition of powdered magnesium stored in bulk form could take place at ambient temperatures much below those reported above [8]. Reynolds and Williams have proposed [9] that the self-ignition behavior of magnesium and other metals is closely related to the low temperature oxidation corrosion of the metal.

### Fire Prevention

As with other combustibles, there is little that can be done to prevent the combustion of magnesium and its alloys when exposed to heat or fire in the presence of oxygen. Means can, however, be devised to reduce the ease with which ignition can occur. The relatively high thermal conductivity of these metals can result in high heat losses from the portion of a specimen which may be exposed to an ignition source. Thus when exposed in sheet form to a given ignition source, the ease of ignition will be related in an inverse manner to the thickness of the material.

Another factor influencing the combustion behavior of magnesium is the ability of the oxide film, formed on the metal surface when exposed to high temperatures, to support and contain the molten metal. Here again, thin sheets of magnesium are more susceptible to sustained combustion than are heavy ones. Work done at Underwriters' Laboratories [10] has resulted in the recommendation that a minimum thickness of 0.080 in. be required for magnesium sheet material proposed as enclosure for electrical appliances. If, however, the magnesium is in the form of a rod there is evidence that considerably heavier sections may support combustion when burned in the inverted position.

Another method which has been proposed for delaying ignition of magnesium parts involves the use [11] of a special anodizing process followed by zinc chromate primer and paint finish. Six inch square sheets of 0.1 in. thickness when so treated showed delays to ignition, after application of a torch flame, of more than thirty times those observed with similar but untreated specimens. This treatment appears to form a tough but flexible envelope which contains the molten magnesium. Methods such as these seem definitely worthwhile from the standpoint of fire safety, but seem unlikely to result in prevention of all such fires.



## Fires - Extinguishment

During combustion of magnesium and many of its alloys, the high temperatures involved results in melting and boiling of a portion of the metallic fuel. Because of this and its low specific gravity, it seems probable that when a water stream or that of any other liquified or solidified gas is directed at the fire, the molten metal is spread about exposing it to air and immediate violent burning. The hot magnesium may cause dissociation of water vapor with which it comes in contact releasing hydrogen as a decomposition product. It is possible that, under suitable conditions, (including those of limited water supply) recombination of this hydrogen with oxygen from the ambient atmosphere can result in serious explosions.

At elevated temperatures the reactivity of magnesium is so great that nitrogen and carbon dioxide are decomposed and combine with the metal. The reaction with these usually inert gases is a comparatively mild one and normally proceeds at lower temperatures than the oxidation reaction. Experiments with small magnesium fires indicate that, under certain conditions, the reduction of reaction temperature and heat release may warrant their use where complete flooding is practical. Thus experiments with small magnesium fires showed that the brilliant flame was immediately extinguished when burning magnesium was immersed in an atmosphere of  $\text{CO}_2$ . The molten magnesium was observed to cool but continue to react with the formation of the oxide, carbon, and possibly also carbon monoxide. Theoretical considerations indicate that this reaction is accompanied with a release of heat on the order 60 percent of that for the reaction in air. Similar experiments involving the flooding of a compartment, within which magnesium was burning, with  $\text{N}_2$  resulted in rapid reduction and disappearance of the flame followed by cooling of the molten metal. For small fires the continuing reaction with formation of the nitride proceeded so slowly that the reaction was in some cases terminated. The heat release during this reaction, when maintained, has been estimated to be on the order of 25 percent of that for the reaction in air. The behavior of magnesium in such atmospheres together with a cooling and smothering effect seems to form the basis of operation of combustible materials which have been suggested [12] for control of magnesium fires. These include graphite, powdered pitch and heavy mineral oil. Other materials such as powdered volcanic ash, flux, dry sand and sodium chloride [12] are probably effective primarily to the degree with which they reduce the access of oxygen to the burning metal and act, as heat sinks, to assist in cooling the molten mass.



Experiments recently performed with liquid  $N_2$  indicate that when properly applied to magnesium fires it is highly effective for their extinguishment. Fires involving as much as five pounds of magnesium turnings as formed in a four-foot metal tub were completely extinguished with less than a gallon of liquid nitrogen.

Recently, several new extinguishing agents have been proposed for use on magnesium fires. Trimethoxyboroxine has been used for this purpose by the Navy 137. Work done for the Air Force has resulted in the proposal that tricresyl phosphate, or a 9-17 percent mixture of boric acid in trethylene glycol 147 be used for such fires. Each of these, when applied, results in the development of secondary fires which apparently have the merit of removing oxygen from the atmosphere surrounding the burning magnesium. In addition, these materials are said to form a flux coating around the molten mass thus largely excluding oxygen and permitting the metal to cool below the ignition temperature.

The usefulness of  $N_2$ ,  $CO_2$  for control of magnesium fires appears to have been overlooked. The reason for this is probably the fact that such gases can only be counted on reducing the heat of the reaction and do not necessarily prevent its completion. These gases do, however, reduce the temperature of the burning magnesium and permit its safe attack with other extinguishing agents which may be used to smother or cool the burning metal to temperatures below the kindling point. The use of liquified  $N_2$  as an extinguishing agent for such fires apparently has not been considered.



## REFERENCES

1. "Thermodynamics Properties of the Elements" Stull & Sinke ACS Monograph (1956).
2. "The Thermodynamic and Physical Properties of the Elements" L. Brewer in "The Chemistry and Metallurgy of Miscellaneous Materials: Thermodynamics" L. L. Quill, McGraw Hill (1950).
3. "Vapor Pressure Measurements on High Boiling Point Metals" E. Baur and R. Brunner, Helvetica Chimica Acta. 17 pp. 958-969. (1934).
4. "The Combustion of Metals" Aristid V. Grosse and Joseph B. Conway, Research Institute of Temple University, First Technical Report High Temperature Project Contract No. 9 onr 87301 (Oct 15, 1951).
5. "Magnesium Alloys and Products" The Dow Chemical Company
6. "Ignition Temperatures of Magnesium and Magnesium Alloys" W. M. Fassell, Jr., L. B. Gulbransen, J. R. Lewis and J. H. Hamilton, J Inst Metals Trans. 3 pp. 522-528. (1951)
7. Private Communication - N. P. Setchkin
8. "Self-Ignition Temperatures of Materials from Kinetic Reaction Data." D. Gross and A. F. Robertson, J Research NBS, V 61, pp. 413-417. (Nov 1958)
9. "An Investigation of the Ignition Temperatures of Solid Metals, Summary Report, W. C. Reynolds, Department of Mechanical Engineering, Stanford University. (June 15, 1957)
10. "A Determination of the Acceptability of Magnesium Alloys as Enclosures for Portable Electrical Appliances" G. Quayle. Bulletin of Research No. 45, (1951). Underwriters' Laboratories, Inc.
11. Private Communication, The Dow Chemical Co.
12. "Magnesium" NSC Data Sheet No. 426. Annon. National Safety News 73-33-40. (Feb 1955).
13. "The Use of Trimethoxyboroxine for the Extinguishment of Metal Fires Part 1 Magnesium" R. L. Tune, R. L. Gipe, H. B. Peterson and R. R. Neill, Naval Research Laboratory Report 4933 (July 1957)
14. "Extinguishing Magnesium Fires" C. H. Yuill. Fire Engineering 108 pp. 1082-1083. (1955)





U. S. DEPARTMENT OF COMMERCE

Lewis L. Strauss, *Secretary*

NATIONAL BUREAU OF STANDARDS

A. V. Astin, *Director*



## THE NATIONAL BUREAU OF STANDARDS

The scope of activities of the National Bureau of Standards at its headquarters in Washington, D. C., and its major laboratories in Boulder, Colo., is suggested in the following listing of the divisions and sections engaged in technical work. In general, each section carries out specialized research, development, and engineering in the field indicated by its title. A brief description of the activities, and of the resultant publications, appears on the inside front cover.

### WASHINGTON, D. C.

- Electricity and Electronics.** Resistance and Reactance. Electron Devices. Electrical Instruments. Magnetic Measurements. Dielectrics. Engineering Electronics. Electronic Instrumentation. Electrochemistry.
- Optics and Metrology.** Photometry and Colorimetry. Optical Instruments. Photographic Technology. Length. Engineering Metrology.
- Heat.** Temperature Physics. Thermodynamics. Cryogenic Physics. Rheology. Engine Fuels. Free Radicals Research.
- Atomic and Radiation Physics.** Spectroscopy. Radiometry. Mass Spectrometry. Solid State Physics. Electron Physics. Atomic Physics. Neutron Physics. Radiation Theory. Radioactivity. X-rays. High Energy Radiation. Nucleonic Instrumentation. Radiological Equipment.
- Chemistry.** Organic Coatings. Surface Chemistry. Organic Chemistry. Analytical Chemistry. Inorganic Chemistry. Electrodeposition. Molecular Structure and Properties of Gases. Physical Chemistry. Thermochemistry. Spectrochemistry. Pure Substances.
- Mechanics.** Sound. Mechanical Instruments. Fluid Mechanics. Engineering Mechanics. Mass and Scale. Capacity, Density, and Fluid Meters. Combustion Controls.
- Organic and Fibrous Materials.** Rubber. Textiles. Paper. Leather. Testing and Specifications. Polymer Structure. Plastics. Dental Research.
- Metallurgy.** Thermal Metallurgy. Chemical Metallurgy. Mechanical Metallurgy. Corrosion. Metal Physics.
- Mineral Products.** Engineering Ceramics. Glass. Refractories. Enameled Metals. Concreting Materials. Constitution and Microstructure.
- Building Technology.** Structural Engineering. Fire Protection. Air Conditioning, Heating, and Refrigeration. Floor, Roof, and Wall Coverings. Codes and Safety Standards. Heat Transfer.
- Applied Mathematics.** Numerical Analysis. Computation. Statistical Engineering. Mathematical Physics.
- Data Processing Systems.** SEAC Engineering Group. Components and Techniques. Digital Circuitry. Digital Systems. Analog Systems. Application Engineering.
- Office of Basic Instrumentation.
  - Office of Weights and Measures.

### BOULDER, COLORADO

- Cryogenic Engineering.** Cryogenic Equipment. Cryogenic Processes. Properties of Materials. Gas Liquefaction.
- Radio Propagation Physics.** Upper Atmosphere Research. Ionospheric Research. Regular Propagation Services. Sun-Earth Relationships. VHF Research. Ionospheric Communication Systems.
- Radio Propagation Engineering.** Data Reduction Instrumentation. Modulation Systems. Navigation Systems. Radio Noise. Tropospheric Measurements. Tropospheric Analysis. Radio Systems Application Engineering. Radio-Meteorology.
- Radio Standards.** High Frequency Electrical Standards. Radio Broadcast Service. High Frequency Impedance Standards. Electronic Calibration Center. Microwave Physics. Microwave Circuit Standards.

