



Electrical and Optical Response Properties of MEH-PPV Semiconductor Polymer Schottky Diodes

by Fred Semendy, Greg Meissner, and Priyalal Wijewarnasuriya

ARL-TR-5591

July 2011

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Adelphi, MD 20783-1197

ARL-TR-5591

July 2011

Electrical and Optical Response Properties of MEH-PPV Semiconductor Polymer Schottky Diodes

Fred Semendy, Greg Meissner, and Priyalal Wijewarnasuriya
Sensors and Electron Devices Directorate, ARL

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188		
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY) July 2011		2. REPORT TYPE Final		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE Electrical and Optical Response Properties of MEH-PPV Semiconductor Polymer Schottky Diodes		5a. CONTRACT NUMBER			
		5b. GRANT NUMBER			
		5c. PROGRAM ELEMENT NUMBER			
6. AUTHOR(S) Fred Semendy, Greg Meissner, and Priyalal Wijewarnasuriya		5d. PROJECT NUMBER			
		5e. TASK NUMBER			
		5f. WORK UNIT NUMBER			
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: RDRL-SEE-I 2800 Powder Mill Road Adelphi, MD 20783-1197		8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-5591			
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)		10. SPONSOR/MONITOR'S ACRONYM(S)			
		11. SPONSOR/MONITOR'S REPORT NUMBER(S)			
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT Diodes made with poly(2-methoxy-5(2'-ethyl)hexoxy-phenylenevinylene) (MEH-PPV) using indium tin oxide (ITO) as anode and aluminum (Al) as cathode have been fabricated and investigated for current-voltage (I-V) characteristics and optical responsivity. The diode exhibits non-ideal behavior with ideality factor of 0.85 eV. The I-V characteristics of the ITO/MEH-PPV/Al diode without light and with different illumination intensities give an open circuit voltage (V_{oc}) and a short circuit current of (I_{sc}). This suggests that that this diode is a photovoltaic under light illumination. Variations in the responsivity indicate that the ITO/MEH-PPV/Al device is a photo-sensitive diode.					
15. SUBJECT TERMS MEH-PPV, polymer, diode, Schottky					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 14	19a. NAME OF RESPONSIBLE PERSON Fred Semendy
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			19b. TELEPHONE NUMBER (Include area code) (301) 394-4627

Contents

List of Figures	iv
1. Introduction	1
2. Experimental	1
3. Results and Discussion	3
4. Conclusion	5
5. References	6
Distribution List	7

List of Figures

Figure 1. (a) Chemical structure of MEH-PPV and (b) a schematic diagram of ITO/MEH-PPV/Al Schottky diode.	2
Figure 2. I-V characteristics of a ITO/MEH-PPV/Al Schottky diode.	2
Figure 3. Plot of $dV/d\ln(I)$ vs. I for the ITO/MEH-PPV/Al diode.	4
Figure 4. Plot of photocurrent time for a constant voltage (I-V-t) for the ITO/MEH-PPV/Al diode.	4
Figure 5. Plot of photocurrent vs. light intensity of the ITO/MEH-PPV/Al diode.	5

1. Introduction

The usage of soluble conjugate polymers as active materials in optoelectronic applications has opened up the possibility of fabricating many different devices. Soluble conjugated polymers, with their advantage of low cost, flexibility, and high absorption coefficient, have shown the possibility for photodetection and photovoltaic applications. Over the years, the power conversion efficiency has been increasing steadily and rapidly (1–4). Organic semiconductors have been extensively used in electronic devices as active components. Conjugated polymers, known as organic semiconductors with electronic properties, have a wide application in electronic technology. In the past few years, poly(2-methoxy-5(2'-ethyl)hexoxy-phenylenevinylene) (MEH-PPV) has been considered as one of the potential and useful conducting polymers for various optoelectronic applications, such as sensors and organic solar cells, and organic light emitting diodes (OLED) because of its environmental stability and easy conductivity properties. The MEH-PPV acts as an electron donor (p-type semiconducting polymer) with a relatively low conductivity due to its low hole and electron mobilities when compared to inorganic semiconductor materials (5).

The fabrication and characterization of the Schottky diodes using organic semiconductor MEH-PPVs and their derivatives have commanded considerable attention in recent years (6, 7). The device performance of a Schottky diode depends on electrical and electronic characteristics of metal organic semiconductor junction. In this study, an indium-doped tin oxide (ITO)/MEH-PPV/aluminum (Al) Schottky diode was fabricated. The electronic properties, such as barrier height, ideality factor, series resistance, interface properties and the optical response behavior of the diode, are reported.

2. Experimental

The semiconducting polymer MEH-PPV was purchased from Sigma Aldrich Company. The ITO coated on glass substrate was obtained from Merck with a sheet resistance of $20\ \Omega\ \text{cm}$, a thickness of 100 nm, and a transmittance of about 80% in the visible. The ITO substrate was cleaned in an ultrasonic bath of acetone for 20 min, followed by isopropyl alcohol (IPA) rinsing for 20 min at room temperature, before being dried in a nitrogen gas flow. MEH-PPV solutions were prepared in chloroform or 1,2 dichlorobenzene solvents separately at a concentration of 15 mg/ml. The solutions were mixed for 2 h by sonicating. Before spin casting the MEH-PPV solution, part of the ITO was masked for future metal contacts for wire bonding. The MEH-PPV solution was spin cast on an ITO/glass plate at 3000 rpm for 40 s. The film was dried at $50\ ^\circ\text{C}$ for 10 min on a hot plate to evaporate the solvent. Film thickness was measured using a KLA-

Tencor 15 and found to be ~ 200 nm. The film was immediately placed in CHA e-beam evaporator for the metal deposition. At a vacuum of 2×10^{-6} Torr, a 200-nm-thick Al film was deposited on top of the MEH-PPV layer. Figure 1 shows (a) the chemical structure of MEH-PPV and (b) the fabricated MH-PPV diode.




Figure 1. (a) Chemical structure of MEH-PPV and (b) a schematic diagram of ITO/MEH-PPV/Al Schottky diode.

Figure 2 provides the current-voltage (I-V) characteristics of the ITO/MEH-PPV/Al diode.




Figure 2. I-V characteristics of a ITO/MEH-PPV/Al Schottky diode.

3. Results and Discussion

I-V measurements shown in figure 2 were made with Agilent 4156 C parametric analyzer. The diode shows a rectifying behavior and the rectification ratio, which is the ratio of the forward current to reverse current at the certain voltage, was found to be 2.22×10^5 at ± 3 V. The I-V characteristics of the diode can be expressed by the following relation (7, 8):

$$I = I_0 \exp\left(\frac{q(V-IR_s)}{nkT}\right) \left[1 - \exp\left(\frac{q(V-IR_s)}{kT}\right)\right], \quad (1)$$

where R_s is the series resistance, V is the applied voltage, n is the ideality factor, k is the Boltzmann constant, T is the temperature, and I_0 is the reverse saturation current given by

$$I_0 = AA^{**} T^2 \exp\left(-\frac{q\phi_B}{kT}\right), \quad (2)$$

where ϕ_B is the barrier height and A is the contact area, and A^{**} is the Richardson constant.

The diode indicates a non-ideal behavior due to the series resistance. For low voltages, the diode exhibits a linear behavior, but at higher voltages it deviates due to the series resistance and interface state density. To determine the diode parameters, Cheung's method (9, 10) was used to determine the diode's parameters. Cheung's functions are defined as follows:

$$\frac{dV}{d\ln(I)} = n\frac{kT}{q} + IR_s \quad (3)$$

and

$$H(I) = V - n\frac{kT}{q} \ln\left(\frac{I_0}{AA^{**} T^2}\right) = IR_s + n\phi_B. \quad (4)$$

The plots of $\frac{dV}{d\ln(I)}$ versus I are given on figure 3 and show a straight line behavior due to the series resistance region. The series resistance is found to be higher due to the resistance of the polymer MEH-PPV organic semiconductor. The polymeric semiconductor has low mobility and electrical conductivity with respect to an inorganic semiconductor.




Figure 3. Plot of $\frac{dV}{d\ln(I)}$ vs. I for the ITO/MEH-PPV/Al diode.

The photoresponse on/off characteristics of ITO/MEH-PPV/Al diode under different illuminations for a voltage of 0.8 V on a timed scale (I-V-t) are shown in figure 4. The diode exhibits a good photoconductivity response and shows a sudden change as the light turns on. This behavior is abrupt and the increase is noticeable in very short time, and the photocurrent under light shows a stable plateau value. The photocurrent was found to be 2.01 μA at 0.8 V for an optical power of 10 mW, whereas the dark current was nearly 0.26 μA without light. Thus, the photocurrent was nearly 1.8 μA more than the dark current of the diode with the light on. This shows that the photocurrent is drastically increased.




Figure 4. Plot of photocurrent time for a constant voltage (I-V-t) for the ITO/MEH-PPV/Al diode.

Figure 5 gives the photoresponsivity for various light intensities. In each case, the calculated responsivity was 2×10^{-4} A/W for a 10-mW light, 1.1×10^{-4} A/W for 20-mW light, and 0.8×10^{-4} A/W a 30-mW light. This indicates that the responsivity is decreasing as the power of the light is increased. However, to increase the photoconductive properties, one may use blended structures with fullerene or methanofullerene 6,6-phenyl C-61-butyric acid methyl ester (PCBM) as well as use additional light enhancement techniques such as harnessing the plasmonic properties of silver or gold nanoparticles on the substrate.




Figure 5. Plot of photocurrent vs. light intensity of the ITO/MEH-PPV/Al diode.

4. Conclusion

MEH-PPV was used with ITO as anode and Al as cathode to fabricate diodes. The fabricated devices were investigated for I-V characteristics and optical responsivity. The diode exhibited non-ideal behavior with an ideality factor of 0.85 eV. The I-V characteristics of the ITO/MEH-PPV/Al diode without light and with different illumination intensities give an open circuit voltage (V_{oc}) and a short circuit current of (I_{sc}). This result suggests that this diode is photovoltaic under light illumination. Additionally, variations in the responsivity indicate that the ITO/MEH-PPV/Al device is a photo-sensitive diode. Studies of the electrical properties indicate that the photoconductive properties can be further improved by using blended materials (fullerene or PCBM) and incorporating plasmonic properties of silver or gold nanoparticles to enhance the absorption of light.

5. References

1. Stallinga, P.; Gomes, H. L.; Murgia, M.; Mullen, K. *Org. Electro* **2002**, 3, 43.
2. Lei, J.; Liang, W.; Brumlik, C. J.; Mattlin, C. R. *Synth. Met* **1992**, 47, 351.
3. Hall, J.J.M.; Walsh, C. A.; Greenham, N. C.; Maserghia, E. A.; Friend, R. H.; Moratti, S. C.; Holmes, A. B. *Nature* **1995**, 376, 498.
4. Yu, G.; Gao, J.; Hummelen, J. C.; Wudl, F. A.; Heeger, J. *Science* **1995**, 270, 1789.
5. Aydin, M. E.; Yakuphanoglu, F.; Eom, J. H.; Hwang, D. H. *Physica B* **2007**, 387, 239.
6. Willander, M.; Assadi, A.; Svensson, C. *Synth. Met* **1993**, 55, 4099.
7. Rhoderick, E. H.; Williams, R. H. *Metal-Semiconductor Contacts*; Clarendon: Oxford, 1988.
8. Okur, S.; Yakuphanoglu, F.; Ozoz, M.; Kadayiffcilar, P. K. *Microelectron. Eng* **2009**, 86, 2305.
9. Cheung, S. K.; Cheung, N. W. *Appl. Phys. Lett.* **1986**, 49, 85.
10. Pierret, R. F. *Semiconductor Device Fundamentals*; Addison Wesley Publishing Company: New York, 1996

NO. OF COPIES	ORGANIZATION	NO. OF COPIES	ORGANIZATION
1 ELECT	ADMNSTR DEFNS TECHL INFO CTR ATTN DTIC OCP 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218	1	US GOVERNMENT PRINT OFF DEPOSITORY RECEIVING SECTION ATTN MAIL STOP IDAD J TATE 732 NORTH CAPITOL ST NW WASHINGTON DC 20402
1	DARPA MTO ATTN N DHAR 3701 NORTH FAIRFAX DR ARLINGTON VA 22203-1714	1	GENERAL TECHNICAL SERVICES ATTN G P MEISSNER 3100 ROUTE 138 WALL NJ 07719
1 CD	OFC OF THE SECY OF DEFNS ATTN ODDRE (R&AT) THE PENTAGON WASHINGTON DC 20301-3080	1	DIRECTOR US ARMY RSRCH LAB ATTN RDRL ROE L W CLARK PO BOX 12211 RESEARCH TRIANGLE PARK NC 27709
1	US ARMY RSRCH DEV AND ENGRG CMND ARMAMENT RSRCH DEV & ENGRG CTR ARMAMENT ENGRG & TECHN LGY CTR ATTN AMSRD AAR AEF T J MATTS BLDG 305 ABERDEEN PROVING GROUND MD 21005-5001	62	U.S. ARMY RSRCH LAB ATTN IMNE ALC HRR MAIL & RECORDS MGMT ATTN RDRL CIO LL TECHL LIB ATTN RDRL CIO MT TECHL PUB ATTN RDRL SE T BOWER ATTN RDRL SE J PELLEGRINO ATTN RDRL SED E B MORGAN ATTN RDRL SED E K A JONES ATTN RDRL SED E M LITZ ATTN RDRL SED P A LELIS ATTN RDRL SEE E K ALIBERTI ATTN RDRL SEE E N GUPTA ATTN RDRL SEE E R TOBER ATTN RDRL SEE E T ALEXANDER ATTN RDRL SEE G WOOD ATTN RDRL SEE I S TRIVEDI ATTN RDRL SEE I B ZANDI ATTN RDRL SEE I D BEEKMAN ATTN RDRL SEE I F SEMENDY (5 COPIES) ATTN RDRL SEE I G BRILL ATTN RDRL SEE I J LITTLE ATTN RDRL SEE I K K CHOI ATTN RDRL SEE I K OLVER ATTN RDRL SEE I P FOLKES ATTN RDRL SEE I P TAYLOR ATTN RDRL SEE I P UPPAL ATTN RDRL SEE I S FARRELL (3 COPIES) ATTN RDRL SEE I S SVENSSON ATTN RDRL SEE I W BECK
3	CECOM NVESD ATTN AMSEL RD NV ATTN AMSEL RD NV A SCHOLTZ ATTN AMSEL RD NV D BENSON 10221 BURBECK RD STE 430 FT BELVOIR VA 22060-5806		
1	PM TIMS, PROFILER (MMS-P) AN/TMQ-52 ATTN B GRIFFIES BUILDING 563 FT MONMOUTH NJ 07703		
1	US ARMY INFO SYS ENGRG CMND ATTN AMSEL IE TD A RIVERA FT HUACHUCA AZ 85613-5300		
1	COMMANDER US ARMY RDECOM ATTN AMSRD AMR W C MCCORKLE 5400 FOWLER RD REDSTONE ARSENAL AL 35898-5000		

NO. OF COPIES	ORGANIZATION
------------------	--------------

	ATTN RDRL SEE I W SARNEY
	ATTN RDRL SEE I Y CHEN
	ATTN RDRL SEE L BLISS
	ATTN RDRL SEE M G DANG
	ATTN RDRL SEE M G GARRETT
	ATTN RDRL SEE M M REED
	ATTN RDRL SEE M
	M TAYSING-LARA
	ATTN RDRL SEE M M WRABACK
	ATTN RDRL SEE M N BAMBHA
	ATTN RDRL SEE M N DAS
	ATTN RDRL SEE M P SHEN
	ATTN RDRL SEE M W CHANG
	ATTN RDRL SEE O N FELL
	ATTN RDRL SEE O P PELLEGRINO
	ATTN RDRL SEE P GILLESPIE
	ATTN RDRL SEG N MARK
	(3 COPIES)
	ATTN RDRL SER E A DARWISH
	ATTN RDRL SER E P SHAH
	ATTN RDRL SER L A WICKENDEN
	ATTN RDRL SER L B NICHOLS
	ATTN RDRL SER L E ZAKAR
	ATTN RDRL SER L M DUBEY
	ATTN RDRL SER L M ERVIN
	ATTN RDRL SER L S KILPATRICK
	ATTN RDRL SER P AMIRTHARAJ
	ATTN RDRL SER U C FAZI
	ADELPHI MD 20783-1197

TOTAL: 75 (73 HCS, 1 CD, 1 ELECT)